

CERTIFICATE OF ANALYSIS FOR
LOW GRADE COPPER ORE REFERENCE MATERIAL
OREAS 923

Table 1. Certified Values, SDs, 95% Confidence and Tolerance Limits for OREAS 923

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
4-Acid Digestion						
Ag, Silver (ppm)	1.60	0.21	1.52	1.69	1.42	1.79
Al, Aluminium (wt.%)	7.29	0.383	7.09	7.48	7.07	7.50
As, Arsenic (ppm)	7.61	0.82	7.39	7.83	6.99	8.23
Ba, Barium (ppm)	434	16.8	426	442	422	445
Be, Beryllium (ppm)	2.42	0.30	2.27	2.57	2.28	2.56
Bi, Bismuth (ppm)	21.4	2.5	20.4	22.3	18.9	23.8
Ca, Calcium (wt.%)	0.473	0.019	0.464	0.482	0.456	0.491
Cd, Cadmium (ppm)	0.42	0.05	0.39	0.45	0.40	0.44
Ce, Cerium (ppm)	83	4.8	80	86	81	85
Co, Cobalt (ppm)	23.1	1.54	22.4	23.7	22.2	23.9
Cr, Chromium (ppm)	71	8	68	75	68	75
Cs, Cesium (ppm)	6.70	0.451	6.45	6.95	6.55	6.85
Cu, Copper (ppm)	4230	223.6	4159	4301	4053	4408
Dy, Dysprosium (ppm)	5.05	0.237	4.87	5.23	4.87	5.23
Er, Erbium (ppm)	2.86	0.120	2.76	2.95	2.76	2.96
Eu, Europium (ppm)	1.37	0.057	1.32	1.41	1.33	1.40
Fe, Iron (wt.%)	6.43	0.348	6.26	6.60	6.29	6.57
Ga, Gallium (ppm)	20.3	1.04	19.8	20.8	19.7	20.9
Gd, Gadolinium (ppm)	5.73	0.311	5.47	5.98	5.56	5.90
Ge, Germanium (ppm)	< 2	IND	IND	IND	IND	IND
Hf, Hafnium (ppm)	3.42	0.203	3.32	3.52	3.28	3.56
Hg, Mercury (ppm)	< 1	IND	IND	IND	IND	IND
Ho, Holmium (ppm)	0.96	0.044	0.94	0.99	0.93	1.00
In, Indium (ppm)	0.52	0.032	0.50	0.54	0.49	0.55
K, Potassium (wt.%)	2.51	0.057	2.49	2.53	2.45	2.58
La, Lanthanum (ppm)	42.2	2.03	41.1	43.3	41.1	43.3
Li, Lithium (ppm)	31.4	2.09	30.3	32.4	30.0	32.8
Lu, Lutetium (ppm)	0.39	0.034	0.37	0.42	0.37	0.42
Mg, Magnesium (wt.%)	1.69	0.079	1.65	1.73	1.66	1.73

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
4-Acid Digestion continued						
Mn, Manganese (wt.%)	0.095	0.004	0.093	0.096	0.092	0.097
Mo, Molybdenum (ppm)	0.93	0.092	0.88	0.98	0.85	1.02
Na, Sodium (wt.%)	0.324	0.017	0.316	0.333	0.314	0.335
Nb, Niobium (ppm)	14.1	0.90	13.7	14.5	13.6	14.6
Nd, Neodymium (ppm)	35.4	1.40	34.3	36.5	34.6	36.1
Ni, Nickel (ppm)	35.8	2.48	34.7	36.9	34.6	37.1
P, Phosphorus (wt.%)	0.063	0.004	0.061	0.064	0.060	0.065
Pb, Lead (ppm)	83	3.7	82	85	80	87
Pr, Praseodymium (ppm)	9.58	0.345	9.30	9.85	9.38	9.78
Rb, Rubidium (ppm)	166	10.8	159	172	161	170
Re, Rhenium (ppb)	< 2	IND	IND	IND	IND	IND
S, Sulphur (wt.%)	0.691	0.024	0.680	0.702	0.666	0.716
Sb, Antimony (ppm)	1.29	0.102	1.24	1.34	1.23	1.34
Sc, Scandium (ppm)	13.1	0.83	12.6	13.6	12.7	13.5
Se, Selenium (ppm)	6.54	1.13	5.92	7.16	5.52	7.56
Sm, Samarium (ppm)	6.64	0.358	6.36	6.92	6.44	6.84
Sn, Tin (ppm)	13.3	0.95	12.8	13.7	13.0	13.6
Sr, Strontium (ppm)	43.0	2.54	41.7	44.3	41.6	44.4
Ta, Tantalum (ppm)	1.11	0.16	1.03	1.20	1.03	1.19
Tb, Terbium (ppm)	0.85	0.044	0.82	0.88	0.83	0.88
Te, Tellurium (ppm)	< 0.05	IND	IND	IND	IND	IND
Th, Thorium (ppm)	16.5	1.26	15.8	17.2	16.0	16.9
Ti, Titanium (wt.%)	0.405	0.024	0.393	0.416	0.392	0.417
Tl, Thallium (ppm)	0.86	0.049	0.83	0.88	0.83	0.88
Tm, Thulium (ppm)	0.41	0.032	0.39	0.43	0.39	0.43
U, Uranium (ppm)	3.06	0.158	2.98	3.15	2.98	3.15
V, Vanadium (ppm)	91	5.8	89	94	89	94
W, Tungsten (ppm)	4.85	0.58	4.62	5.09	4.37	5.33
Y, Yttrium (ppm)	26.4	1.65	25.4	27.3	25.7	27.0
Yb, Ytterbium (ppm)	2.57	0.121	2.49	2.64	2.48	2.65
Zn, Zinc (ppm)	345	10.9	341	350	336	355
Zr, Zirconium (ppm)	116	13	109	122	112	119
Aqua Regia Digestion						
Ag, Silver (ppm)	1.62	0.18	1.55	1.68	1.40	1.83
Al, Aluminium (wt.%)	2.80	0.130	2.73	2.86	2.74	2.86
As, Arsenic (ppm)	7.07	0.71	6.75	7.38	6.73	7.40
Au, Gold (ppb)	< 5	IND	IND	IND	IND	IND
B, Boron (ppm)	< 10	IND	IND	IND	IND	IND
Ba, Barium (ppm)	54*	3.6*	53*	56*	51*	58*
Be, Beryllium (ppm)	0.61	0.08	0.56	0.66	0.55	0.66
Bi, Bismuth (ppm)	21.8	1.73	21.3	22.3	19.2	24.3

*Statistics presented above for Ba via aqua regia digestion are based on a consensus of 11 labs. A second consensus of 5 labs exists at ~79ppm with a 1RSD of 15%. This data separation was necessary due to the bi-modal nature of the results received.

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Aqua Regia Digestion continued						
Ca, Calcium (wt.%)	0.326	0.016	0.317	0.335	0.311	0.342
Cd, Cadmium (ppm)	0.40	0.027	0.39	0.41	0.38	0.42
Ce, Cerium (ppm)	60	6	56	64	58	61
Co, Cobalt (ppm)	22.2	1.17	21.6	22.7	21.5	22.8
Cr, Chromium (ppm)	39.4	1.97	38.5	40.4	38.0	40.8
Cs, Cesium (ppm)	1.56	0.21	1.42	1.69	1.49	1.62
Cu, Copper (ppm)	4248	141.5	4205	4292	4058	4438
Dy, Dysprosium (ppm)	< 5	IND	IND	IND	IND	IND
Er, Erbium (ppm)	< 3	IND	IND	IND	IND	IND
Eu, Europium (ppm)	< 2	IND	IND	IND	IND	IND
Fe, Iron (wt.%)	5.91	0.309	5.77	6.06	5.75	6.08
Ga, Gallium (ppm)	8.01	0.486	7.75	8.27	7.76	8.26
Gd, Gadolinium (ppm)	4.07	0.81	3.28	4.86	3.84	4.29
Ge, Germanium (ppm)	< 0.3	IND	IND	IND	IND	IND
Hf, Hafnium (ppm)	0.60	0.09	0.53	0.66	0.57	0.62
Hg, Mercury (ppm)	< 0.1	IND	IND	IND	IND	IND
Ho, Holmium (ppm)	< 1	IND	IND	IND	IND	IND
In, Indium (ppm)	0.45	0.031	0.43	0.46	0.42	0.47
K, Potassium (wt.%)	0.322	0.051	0.295	0.349	0.306	0.339
La, Lanthanum (ppm)	30.0	3.9	27.9	32.1	28.9	31.1
Li, Lithium (ppm)	23.4	1.19	22.8	24.0	22.6	24.3
Lu, Lutetium (ppm)	< 0.3	IND	IND	IND	IND	IND
Mg, Magnesium (wt.%)	1.43	0.048	1.41	1.46	1.40	1.46
Mn, Manganese (wt.%)	0.085	0.003	0.083	0.086	0.083	0.087
Mo, Molybdenum (ppm)	0.84	0.11	0.78	0.90	0.78	0.89
Na, Sodium (wt.%)	< 0.03	IND	IND	IND	IND	IND
Nb, Niobium (ppm)	< 0.5	IND	IND	IND	IND	IND
Nd, Neodymium (ppm)	25.4	4.8	21.3	29.6	23.9	27.0
Ni, Nickel (ppm)	32.7	1.84	31.8	33.6	31.5	33.8
P, Phosphorus (wt.%)	0.061	0.002	0.059	0.062	0.059	0.063
Pb, Lead (ppm)	81	4.8	79	83	79	84
Pr, Praseodymium (ppm)	6.79	0.628	5.96	7.62	6.43	7.15
Rb, Rubidium (ppm)	19.6	2.6	17.7	21.4	18.9	20.2
Re, Rhenium (ppb)	< 1	IND	IND	IND	IND	IND
S, Sulphur (wt.%)	0.684	0.035	0.668	0.700	0.660	0.708
Sb, Antimony (ppm)	0.58	0.09	0.52	0.63	0.54	0.62
Sc, Scandium (ppm)	3.09	0.51	2.78	3.40	2.93	3.25
Se, Selenium (ppm)	5.99	0.84	5.62	6.35	5.49	6.49
Sm, Samarium (ppm)	4.34	0.80	3.56	5.12	4.14	4.53
Sn, Tin (ppm)	5.99	0.573	5.67	6.31	5.75	6.22
Sr, Strontium (ppm)	13.6	0.50	13.3	13.9	13.1	14.1
Ta, Tantalum (ppm)	< 0.02	IND	IND	IND	IND	IND
Tb, Terbium (ppm)	0.54	0.10	0.46	0.62	0.51	0.57

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Aqua Regia Digestion continued						
Te, Tellurium (ppm)	< 0.05	IND	IND	IND	IND	IND
Th, Thorium (ppm)	14.3	0.93	13.8	14.9	13.9	14.8
Ti, Titanium (wt.%)	< 0.2	IND	IND	IND	IND	IND
Tl, Thallium (ppm)	0.12	0.02	0.11	0.14	IND	IND
Tm, Thulium (ppm)	< 0.4	IND	IND	IND	IND	IND
U, Uranium (ppm)	1.80	0.130	1.71	1.89	1.74	1.86
V, Vanadium (ppm)	30.6	2.95	29.0	32.2	29.5	31.8
W, Tungsten (ppm)	1.96	0.22	1.84	2.07	1.65	2.27
Y, Yttrium (ppm)	14.3	2.7	12.8	15.9	13.7	14.9
Zn, Zinc (ppm)	335	12.9	330	341	326	345
Zr, Zirconium (ppm)	22.5	4.0	20.0	24.9	21.0	23.9
Peroxide Fusion ICP						
Al, Aluminium (wt.%)	7.39	0.176	7.27	7.51	7.22	7.56
As, Arsenic (ppm)	< 10	IND	IND	IND	IND	IND
Ba, Barium (ppm)	443	17.1	433	454	429	458
Be, Beryllium (ppm)	< 3	IND	IND	IND	IND	IND
Bi, Bismuth (ppm)	21.2	2.02	20.5	21.9	18.9	23.6
Ca, Calcium (wt.%)	0.488	0.044	0.459	0.517	0.456	0.520
Cd, Cadmium (ppm)	< 1	IND	IND	IND	IND	IND
Ce, Cerium (ppm)	83	5.2	80	86	80	86
Co, Cobalt (ppm)	23.9	1.34	23.0	24.8	22.4	25.4
Cr, Chromium (ppm)	88	11	82	94	83	93
Cs, Cesium (ppm)	6.93	0.237	6.81	7.05	6.72	7.14
Cu, Copper (ppm)	4328	205.1	4250	4407	4114	4543
Dy, Dysprosium (ppm)	5.38	0.277	5.21	5.56	5.21	5.56
Er, Erbium (ppm)	3.15	0.297	2.90	3.39	3.03	3.27
Eu, Europium (ppm)	1.49	0.092	1.42	1.56	IND	IND
Fe, Iron (wt.%)	6.59	0.198	6.48	6.70	6.45	6.74
Ga, Gallium (ppm)	20.7	1.26	19.9	21.5	19.7	21.7
Gd, Gadolinium (ppm)	6.30	0.506	5.88	6.72	6.07	6.53
Hf, Hafnium (ppm)	5.47	0.460	4.87	6.08	IND	IND
Ho, Holmium (ppm)	1.11	0.092	1.04	1.19	IND	IND
In, Indium (ppm)	0.53	0.06	0.49	0.58	IND	IND
K, Potassium (wt.%)	2.54	0.130	2.45	2.63	2.47	2.62
La, Lanthanum (ppm)	43.4	2.47	41.6	45.2	42.1	44.7
Li, Lithium (ppm)	30.8	1.85	29.3	32.2	29.3	32.2
Lu, Lutetium (ppm)	0.45	0.06	0.38	0.53	IND	IND
Mg, Magnesium (wt.%)	1.72	0.073	1.68	1.77	1.69	1.76
Mn, Manganese (wt.%)	0.098	0.003	0.096	0.100	0.096	0.100
Mo, Molybdenum (ppm)	< 1	IND	IND	IND	IND	IND
Nb, Niobium (ppm)	14.5	2.1	12.7	16.2	13.7	15.2
Nd, Neodymium (ppm)	37.1	1.23	36.1	38.0	36.0	38.1
Ni, Nickel (ppm)	40.7	7.9	34.3	47.0	36.4	44.9

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Peroxide Fusion ICP continued						
P, Phosphorus (wt.%)	0.061	0.005	0.057	0.065	0.056	0.066
Pb, Lead (ppm)	86	9	80	93	83	90
Pr, Praseodymium (ppm)	10.1	0.45	9.8	10.5	9.8	10.5
Rb, Rubidium (ppm)	169	6.4	164	174	165	173
S, Sulphur (wt.%)	0.716	0.049	0.709	0.722	0.650	0.781
Sb, Antimony (ppm)	< 2	IND	IND	IND	IND	IND
Si, Silicon (wt.%)	29.67	0.551	29.21	30.12	28.84	30.49
Sm, Samarium (ppm)	7.01	0.250	6.85	7.17	6.74	7.29
Sn, Tin (ppm)	16.1	2.7	13.6	18.5	IND	IND
Sr, Strontium (ppm)	42.9	1.90	41.8	43.9	39.7	46.0
Ta, Tantalum (ppm)	1.21	0.21	1.04	1.39	IND	IND
Tb, Terbium (ppm)	0.97	0.084	0.90	1.04	IND	IND
Te, Tellurium (ppm)	< 1	IND	IND	IND	IND	IND
Th, Thorium (ppm)	16.6	0.96	15.9	17.3	16.0	17.2
Ti, Titanium (wt.%)	0.410	0.020	0.397	0.422	0.397	0.422
Tl, Thallium (ppm)	0.89	0.028	0.87	0.92	IND	IND
Tm, Thulium (ppm)	0.49	0.06	0.43	0.54	IND	IND
U, Uranium (ppm)	3.32	0.158	3.20	3.44	3.20	3.45
V, Vanadium (ppm)	93	5.2	90	96	89	97
W, Tungsten (ppm)	< 7	IND	IND	IND	IND	IND
Y, Yttrium (ppm)	28.6	0.99	27.9	29.3	27.8	29.5
Yb, Ytterbium (ppm)	2.88	0.172	2.75	3.01	2.70	3.06
Zn, Zinc (ppm)	358	23.0	349	367	339	377

Note: intervals may appear asymmetric due to rounding

INTRODUCTION

OREAS reference materials are intended to provide a low cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

SOURCE MATERIAL

OREAS 923 is one of a suite of sixteen copper CRMs (OREAS 920 to OREAS 935) prepared from material from the CSA mine located near the town of Cobar in central western New South Wales, Australia. The copper ore body is hosted by the Early Devonian CSA Siltstone, a thinly bedded turbiditic sequence of carbonaceous siltstones and mudstones with minor coarser units. The CSA Siltstone is part of the Cobar Supergroup, consisting of lower syn-rift sediments and upper post-rift sag phase sediments. The mineralisation is structurally controlled and confined to a number of

steeply dipping bodies within a major shear zone on the eastern margin of the Early Devonian Cobar Basin. It is characterised by low-grade greenschist alteration and epigenetic low-grade mineralisation enveloping higher-grade shoots of vein complexes or sub-massive to massive sulphides. The sulphides include chalcopyrite, pyrrhotite, pyrite, sphalerite, galena, bornite and cubanite. Iron-rich chlorite and silica are prominent alterations in the siltstone host.

COMMINTION AND HOMOGENISATION PROCEDURES

The material constituting OREAS 923 was prepared in the following manner:

- drying to constant mass at 105°C;
- preliminary blending of copper ores and barren siltstone materials;
- multi-stage milling to approximately 99% less than 75 microns;
- final homogenisation;
- packaging in 10g units in laminated foil pouches.

ANALYTICAL PROGRAM

Twenty two commercial analytical laboratories participated in the program to characterise the analytes reported in Table 1. The following methods were employed for method specific certification:

- Four acid (HCl-HNO₃-HF-HClO₄) digestion with ICP-OES, ICP-MS or AAS finish (19 laboratories);
- Aqua regia digestion with ICP-OES, ICP-MS or AAS finish (19 laboratories);
- Peroxide fusion with ICP-OES, ICP-MS or AAS finish (12 laboratories).

For the round robin program ten 300g test units were taken at predetermined intervals during the bagging stage, immediately following final homogenisation, and are considered representative of the entire batch. The six samples received by each laboratory were obtained by taking two 20g scoop splits from each of three separate 300g test units. This format enabled nested ANOVA treatment of the results to evaluate homogeneity, i.e. to ascertain whether between-unit variance is greater than within-unit variance. Table 1 presents the certified values together with their associated 1SD's, 95% confidence and tolerance limits and Table 2 shows indicative values. Table 3 provides performance gate intervals for the certified values of each analytical method group based on their pooled 1SD's. Tabulated results of all elements together with uncorrected means, medians, standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**Datapack for OREAS 923.xlsx**).

STATISTICAL ANALYSIS

Certified Values, Standard Deviations, Confidence and Tolerance Limits have been determined for each analytical method following removal of individual and laboratory outliers (Table 1). Certified Values are the mean of means after outlier filtering. The 95% Confidence Limit is a measure of the reliability of the certified value, i.e. the narrower the

Confidence Interval the greater the certainty in the Certified Value. It should not be used as a control limit for laboratory performance. Indicative values (Table 2) are provided where i) the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification; ii) interlaboratory consensus is poor; or iii) a significant proportion of results are outlying or results are multimodal.

Table 2. Indicative Values for OREAS 923

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
4-Acid Digestion								
B	ppm	8.67	Ru	ppm	< 0.1			
Aqua Regia Digestion								
Pd	ppb	11	Ru	ppm	< 0.005	Yb	ppm	< 2
Pt	ppb	< 5	Si	wt.%	< 0.01			
Infrared Combustion								
S	wt.%	0.733						
Peroxide Fusion ICP								
Ag	ppm	1.39	Re	ppm	< 0.1	Zr	ppm	173
B	ppm	26.7	Sc	ppm	11.9			
Ge	ppm	2.42	Se	ppm	4.06			

Standard Deviation values (1SDs) are reported in Table 1 and provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability. The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e. after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.

Performance Gates (Table 3) are calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned.

A second method utilises a 5% window calculated directly from the certified value. Standard deviation is also shown in relative per cent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow.

Tolerance Limits (ISO Guide 3207) were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of

tolerance limits may be illustrated for copper by 4-acid digestion, where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($p=0.95$) will have concentrations lying between between 4053 and 4408 ppm. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

The homogeneity of OREAS 923 has also been evaluated in an ANOVA study for all certified analytes. This study tests the null hypothesis that no statistically significant difference exists between the *between-unit variance* and the *within-unit variance* (i.e. p-values <0.05 indicate rejection of the null hypothesis). Of the 177 certified values, no failures were observed indicating no evidence to reject the null hypothesis.

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS 923 is fit-for-purpose as a certified reference material (see 'Intended Use' below).

PARTICIPATING LABORATORIES

Accurassay, Thunder Bay, ON, Canada
Acme, Santiago, Chile
Acme, Vancouver, BC, Canada
Actlabs, Ancaster, Ontario, Canada
Actlabs, Kamloops, BC, Canada
Actlabs, Thunder Bay, Ontario, Canada
ALS, Brisbane, QLD, Australia
ALS, Burnie, TAS, Australia
ALS, Loughrea, County Galway, Ireland
ALS, Vancouver, BC, Canada
Amdel (BV), Cardiff, NSW, Australia
Intertek Genalysis, Perth, WA, Australia
Intertek Testing Services, Adelaide, SA, Australia
Intertek Testing Services, Beijing, China
Intertek Testing Services, Jakarta Selatan, Indonesia
Intertek Genalysis, Johannesburg, Sth Africa
Intertek Testing Services, Muntinlupa, Philippines
Labtium Oy, Rovaniemi, Finland
MINTEK, Randburg, Sth Africa
PT. Geoservices, Cikarang, Indonesia
SGS, Booysens, Gauteng, South Africa
SGS Didipio, Makati City, Philippines
SGS, Lakefield, Ontario, Canada
SGS Nui Phao, Ha Noi, Vietnam
SGS, Vancouver, BC, Canada
SGS, Vespasiano, MG, Brazil
Shiva Analyticals, Bangalore North, Karnataka, India
Ultra Trace (BV), Perth, WA, Australia

Table 3. Performance Gates for OREAS 923

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion											
Ag, ppm	1.60	0.21	1.19	2.02	0.99	2.22	12.85%	25.70%	38.54%	1.52	1.69
Al, wt.%	7.29	0.383	6.52	8.05	6.14	8.44	5.26%	10.52%	15.78%	6.92	7.65
As, ppm	7.61	0.82	5.97	9.25	5.14	10.07	10.79%	21.59%	32.38%	7.23	7.99
Ba, ppm	434	17	400	467	383	484	3.87%	7.73%	11.60%	412	456
Be, ppm	2.42	0.30	1.82	3.02	1.51	3.33	12.49%	24.97%	37.46%	2.30	2.54
Bi, ppm	21.4	2.5	16.3	26.4	13.8	29.0	11.87%	23.73%	35.60%	20.3	22.4
Ca, wt.%	0.473	0.019	0.435	0.511	0.416	0.530	3.99%	7.98%	11.97%	0.449	0.497
Cd, ppm	0.42	0.05	0.32	0.52	0.27	0.57	12.20%	24.39%	36.59%	0.40	0.44
Ce, ppm	83	4.8	74	93	69	97	5.76%	11.52%	17.28%	79	87
Co, ppm	23.1	1.54	20.0	26.2	18.5	27.7	6.69%	13.37%	20.06%	21.9	24.2
Cr, ppm	71	8	55	88	47	96	11.60%	23.20%	34.80%	68	75
Cs, ppm	6.70	0.451	5.80	7.60	5.35	8.05	6.72%	13.45%	20.17%	6.37	7.04
Cu, ppm	4230	224	3783	4678	3559	4901	5.29%	10.57%	15.86%	4019	4442
Dy, ppm	5.05	0.237	4.58	5.53	4.34	5.76	4.70%	9.39%	14.09%	4.80	5.30
Er, ppm	2.86	0.120	2.62	3.10	2.50	3.22	4.21%	8.42%	12.62%	2.71	3.00
Eu, ppm	1.37	0.057	1.25	1.48	1.20	1.54	4.17%	8.34%	12.51%	1.30	1.44
Fe, wt.%	6.43	0.348	5.73	7.13	5.39	7.47	5.41%	10.83%	16.24%	6.11	6.75
Ga, ppm	20.3	1.04	18.2	22.4	17.2	23.4	5.11%	10.22%	15.33%	19.3	21.3
Gd, ppm	5.73	0.311	5.10	6.35	4.79	6.66	5.44%	10.88%	16.31%	5.44	6.01
Ge, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	3.42	0.203	3.01	3.82	2.81	4.03	5.93%	11.85%	17.78%	3.25	3.59
Hg, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ho, ppm	0.96	0.044	0.87	1.05	0.83	1.09	4.53%	9.07%	13.60%	0.91	1.01
In, ppm	0.52	0.032	0.46	0.59	0.42	0.62	6.23%	12.46%	18.69%	0.49	0.55
K, wt.%	2.51	0.057	2.40	2.63	2.34	2.68	2.25%	4.51%	6.76%	2.39	2.64
La, ppm	42.2	2.03	38.1	46.3	36.1	48.3	4.82%	9.63%	14.45%	40.1	44.3
Li, ppm	31.4	2.09	27.2	35.6	25.1	37.7	6.66%	13.31%	19.97%	29.8	33.0
Lu, ppm	0.39	0.034	0.33	0.46	0.29	0.50	8.65%	17.31%	25.96%	0.38	0.41
Mg, wt.%	1.69	0.079	1.53	1.85	1.45	1.93	4.69%	9.38%	14.06%	1.61	1.78
Mn, wt.%	0.095	0.004	0.087	0.102	0.084	0.106	3.81%	7.62%	11.42%	0.090	0.099
Mo, ppm	0.93	0.092	0.75	1.12	0.66	1.21	9.81%	19.62%	29.44%	0.89	0.98
Na, wt.%	0.324	0.017	0.290	0.358	0.273	0.375	5.24%	10.48%	15.72%	0.308	0.341

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
Nb, ppm	14.1	0.90	12.3	15.9	11.4	16.8	6.42%	12.83%	19.25%	13.4	14.8
Nd, ppm	35.4	1.40	32.6	38.2	31.2	39.5	3.95%	7.89%	11.84%	33.6	37.1
Ni, ppm	35.8	2.48	30.9	40.8	28.4	43.3	6.91%	13.83%	20.74%	34.1	37.6
P, wt.%	0.063	0.004	0.055	0.071	0.051	0.075	6.40%	12.79%	19.19%	0.060	0.066
Pb, ppm	83	3.7	76	91	72	94	4.38%	8.77%	13.15%	79	87
Pr, ppm	9.58	0.345	8.89	10.27	8.54	10.61	3.60%	7.20%	10.80%	9.10	10.06
Rb, ppm	166	11	144	187	133	198	6.50%	13.00%	19.50%	157	174
Re, ppb	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt.%	0.691	0.024	0.644	0.738	0.620	0.762	3.41%	6.82%	10.24%	0.656	0.726
Sb, ppm	1.29	0.102	1.08	1.49	0.98	1.59	7.94%	15.87%	23.81%	1.22	1.35
Sc, ppm	13.1	0.83	11.4	14.7	10.6	15.6	6.34%	12.69%	19.03%	12.4	13.7
Se, ppm	6.54	1.13	4.28	8.80	3.15	9.93	17.26%	34.52%	51.78%	6.21	6.87
Sm, ppm	6.64	0.358	5.92	7.35	5.56	7.71	5.40%	10.80%	16.20%	6.31	6.97
Sn, ppm	13.3	0.95	11.4	15.2	10.4	16.1	7.18%	14.37%	21.55%	12.6	13.9
Sr, ppm	43.0	2.54	37.9	48.1	35.4	50.6	5.90%	11.79%	17.69%	40.9	45.2
Ta, ppm	1.11	0.16	0.80	1.43	0.64	1.59	14.22%	28.45%	42.67%	1.06	1.17
Tb, ppm	0.85	0.044	0.76	0.94	0.72	0.99	5.21%	10.41%	15.62%	0.81	0.90
Te, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	16.5	1.26	13.9	19.0	12.7	20.3	7.66%	15.33%	22.99%	15.6	17.3
Ti, wt.%	0.405	0.024	0.358	0.452	0.334	0.475	5.81%	11.63%	17.44%	0.385	0.425
Tl, ppm	0.86	0.049	0.76	0.95	0.71	1.00	5.71%	11.42%	17.13%	0.81	0.90
Tm, ppm	0.41	0.032	0.35	0.47	0.32	0.51	7.69%	15.37%	23.06%	0.39	0.43
U, ppm	3.06	0.158	2.75	3.38	2.59	3.54	5.15%	10.30%	15.44%	2.91	3.22
V, ppm	91	5.8	80	103	74	109	6.31%	12.63%	18.94%	87	96
W, ppm	4.85	0.58	3.70	6.01	3.12	6.59	11.92%	23.83%	35.75%	4.61	5.09
Y, ppm	26.4	1.65	23.1	29.7	21.4	31.3	6.27%	12.54%	18.80%	25.0	27.7
Yb, ppm	2.57	0.121	2.32	2.81	2.20	2.93	4.73%	9.46%	14.18%	2.44	2.69
Zn, ppm	345	11	324	367	313	378	3.15%	6.31%	9.46%	328	363
Zr, ppm	116	13	90	141	78	154	10.97%	21.94%	32.91%	110	121
Aqua Regia Digestion											
Ag, ppm	1.62	0.18	1.26	1.97	1.09	2.15	10.94%	21.87%	32.81%	1.54	1.70
Al, wt.%	2.80	0.130	2.54	3.06	2.41	3.19	4.63%	9.27%	13.90%	2.66	2.94

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
As, ppm	7.07	0.71	5.64	8.50	4.93	9.21	10.11%	20.21%	30.32%	6.71	7.42
Au, ppb	< 5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
B, ppm	< 10	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ba, ppm	54*	3.6*	47*	62*	44*	65*	6.69%	13.38%	20.07%	52	57
Be, ppm	0.61	0.08	0.44	0.78	0.36	0.86	13.79%	27.57%	41.36%	0.58	0.64
Bi, ppm	21.8	1.73	18.3	25.2	16.6	27.0	7.96%	15.92%	23.88%	20.7	22.9
Ca, wt.%	0.326	0.016	0.294	0.359	0.277	0.375	5.00%	10.00%	15.00%	0.310	0.343
Cd, ppm	0.40	0.027	0.35	0.46	0.32	0.48	6.63%	13.27%	19.90%	0.38	0.42
Ce, ppm	60	6	48	72	42	78	10.10%	20.19%	30.29%	57	63
Co, ppm	22.2	1.17	19.8	24.5	18.6	25.7	5.28%	10.56%	15.84%	21.0	23.3
Cr, ppm	39.4	1.97	35.5	43.4	33.5	45.3	4.99%	9.97%	14.96%	37.5	41.4
Cs, ppm	1.56	0.21	1.13	1.99	0.91	2.20	13.80%	27.60%	41.40%	1.48	1.63
Cu, ppm	4248	142	3965	4531	3824	4673	3.33%	6.66%	9.99%	4036	4461
Dy, ppm	< 5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Er, ppm	< 3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Eu, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Fe, wt.%	5.91	0.309	5.30	6.53	4.99	6.84	5.22%	10.43%	15.65%	5.62	6.21
Ga, ppm	8.01	0.486	7.04	8.98	6.55	9.47	6.06%	12.12%	18.18%	7.61	8.41
Gd, ppm	4.07	0.81	2.45	5.69	1.64	6.50	19.94%	39.87%	59.81%	3.86	4.27
Ge, ppm	< 0.3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	0.60	0.09	0.41	0.78	0.32	0.88	15.46%	30.92%	46.37%	0.57	0.63
Hg, ppm	< 0.1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ho, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
In, ppm	0.45	0.031	0.39	0.51	0.36	0.54	6.85%	13.70%	20.55%	0.42	0.47
K, wt.%	0.322	0.051	0.221	0.424	0.170	0.474	15.75%	31.51%	47.26%	0.306	0.338
La, ppm	30.0	3.9	22.2	37.8	18.4	41.6	12.93%	25.86%	38.80%	28.5	31.5
Li, ppm	23.4	1.19	21.0	25.8	19.8	27.0	5.09%	10.19%	15.28%	22.3	24.6
Lu, ppm	< 0.3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Mg, wt.%	1.43	0.048	1.34	1.53	1.29	1.58	3.36%	6.72%	10.08%	1.36	1.51
Mn, wt.%	0.085	0.003	0.079	0.091	0.076	0.094	3.64%	7.28%	10.92%	0.081	0.089
Mo, ppm	0.84	0.11	0.62	1.05	0.52	1.16	12.78%	25.56%	38.34%	0.80	0.88

*Statistics presented above for Ba via aqua regia digestion are based on a consensus of 11 labs. A second consensus of 5 labs exists at ~79ppm with a 1RSD of 15%. This data separation was necessary due to the bi-modal nature of the results received.

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Na, wt.%	< 0.03	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nb, ppm	< 0.5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nd, ppm	25.4	4.8	15.9	35.0	11.1	39.7	18.72%	37.44%	56.17%	24.2	26.7
Ni, ppm	32.7	1.84	29.0	36.4	27.2	38.2	5.64%	11.27%	16.91%	31.0	34.3
P, wt.%	0.061	0.002	0.056	0.066	0.053	0.068	4.08%	8.17%	12.25%	0.058	0.064
Pb, ppm	81	4.8	72	91	67	95	5.86%	11.72%	17.57%	77	85
Pr, ppm	6.79	0.628	5.53	8.05	4.91	8.67	9.25%	18.50%	27.74%	6.45	7.13
Rb, ppm	19.6	2.6	14.3	24.8	11.6	27.5	13.48%	26.97%	40.45%	18.6	20.5
Re, ppb	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt.%	0.684	0.035	0.614	0.754	0.579	0.789	5.10%	10.20%	15.30%	0.650	0.718
Sb, ppm	0.58	0.09	0.40	0.76	0.31	0.85	15.50%	31.00%	46.49%	0.55	0.61
Sc, ppm	3.09	0.51	2.07	4.11	1.56	4.62	16.46%	32.93%	49.39%	2.94	3.25
Se, ppm	5.99	0.84	4.30	7.67	3.46	8.52	14.07%	28.13%	42.20%	5.69	6.29
Sm, ppm	4.34	0.80	2.73	5.94	1.93	6.75	18.50%	37.00%	55.51%	4.12	4.55
Sn, ppm	5.99	0.573	4.84	7.13	4.27	7.71	9.58%	19.15%	28.73%	5.69	6.29
Sr, ppm	13.6	0.50	12.6	14.6	12.1	15.1	3.68%	7.37%	11.05%	12.9	14.3
Ta, ppm	< 0.02	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tb, ppm	0.54	0.10	0.34	0.73	0.25	0.83	18.11%	36.21%	54.32%	0.51	0.56
Te, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	14.3	0.93	12.5	16.2	11.5	17.1	6.51%	13.02%	19.53%	13.6	15.1
Ti, wt.%	< 0.2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tl, ppm	0.12	0.02	0.08	0.17	0.06	0.19	18.50%	37.00%	55.50%	0.12	0.13
Tm, ppm	< 0.4	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
U, ppm	1.80	0.130	1.54	2.06	1.41	2.19	7.19%	14.39%	21.58%	1.71	1.89
V, ppm	30.6	2.95	24.7	36.5	21.8	39.5	9.65%	19.29%	28.94%	29.1	32.2
W, ppm	1.96	0.22	1.51	2.41	1.29	2.63	11.43%	22.86%	34.29%	1.86	2.06
Y, ppm	14.3	2.7	8.9	19.8	6.1	22.5	19.05%	38.09%	57.14%	13.6	15.0
Zn, ppm	335	13	310	361	297	374	3.84%	7.68%	11.52%	319	352
Zr, ppm	22.5	4.0	14.5	30.4	10.6	34.4	17.65%	35.30%	52.95%	21.3	23.6
Peroxide Fusion ICP											
Al, wt.%	7.39	0.176	7.04	7.74	6.87	7.92	2.37%	4.75%	7.12%	7.02	7.76
As, ppm	< 10	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion ICP continued											
Ba, ppm	443	17	409	478	392	495	3.86%	7.72%	11.58%	421	466
Be, ppm	< 3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Bi, ppm	21.2	2.02	17.2	25.3	15.2	27.3	9.51%	19.02%	28.53%	20.2	22.3
Ca, wt.%	0.488	0.044	0.401	0.575	0.357	0.618	8.93%	17.86%	26.79%	0.463	0.512
Cd, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ce, ppm	83	5.2	72	93	67	99	6.31%	12.63%	18.94%	79	87
Co, ppm	23.9	1.34	21.2	26.6	19.9	27.9	5.59%	11.19%	16.78%	22.7	25.1
Cr, ppm	88	11	66	109	56	120	12.25%	24.50%	36.76%	84	92
Cs, ppm	6.93	0.237	6.46	7.40	6.22	7.64	3.42%	6.84%	10.26%	6.58	7.28
Cu, ppm	4328	205	3918	4738	3713	4943	4.74%	9.48%	14.21%	4112	4545
Dy, ppm	5.38	0.277	4.83	5.94	4.55	6.21	5.14%	10.28%	15.42%	5.11	5.65
Er, ppm	3.15	0.297	2.55	3.74	2.26	4.04	9.44%	18.88%	28.32%	2.99	3.30
Eu, ppm	1.49	0.092	1.30	1.67	1.21	1.77	6.21%	12.42%	18.63%	1.41	1.56
Fe, wt.%	6.59	0.198	6.20	6.99	6.00	7.19	3.01%	6.02%	9.03%	6.26	6.92
Ga, ppm	20.7	1.26	18.2	23.3	16.9	24.5	6.10%	12.20%	18.30%	19.7	21.8
Gd, ppm	6.30	0.506	5.29	7.31	4.78	7.82	8.03%	16.05%	24.08%	5.99	6.62
Hf, ppm	5.47	0.460	4.55	6.39	4.09	6.85	8.40%	16.81%	25.21%	5.20	5.75
Ho, ppm	1.11	0.092	0.93	1.30	0.84	1.39	8.29%	16.57%	24.86%	1.06	1.17
In, ppm	0.53	0.06	0.42	0.65	0.36	0.70	10.68%	21.36%	32.04%	0.51	0.56
K, wt.%	2.54	0.130	2.28	2.80	2.15	2.93	5.11%	10.23%	15.34%	2.42	2.67
La, ppm	43.4	2.47	38.5	48.4	36.0	50.8	5.69%	11.37%	17.06%	41.3	45.6
Li, ppm	30.8	1.85	27.1	34.4	25.2	36.3	6.00%	12.01%	18.01%	29.2	32.3
Lu, ppm	0.45	0.06	0.34	0.57	0.28	0.62	12.60%	25.21%	37.81%	0.43	0.48
Mg, wt.%	1.72	0.073	1.58	1.87	1.51	1.94	4.25%	8.49%	12.74%	1.64	1.81
Mn, wt.%	0.098	0.003	0.092	0.105	0.088	0.108	3.34%	6.67%	10.01%	0.093	0.103
Mo, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nb, ppm	14.5	2.1	10.3	18.6	8.3	20.7	14.32%	28.63%	42.95%	13.7	15.2
Nd, ppm	37.1	1.23	34.6	39.5	33.4	40.8	3.32%	6.64%	9.97%	35.2	38.9
Ni, ppm	40.7	7.9	24.9	56.4	17.0	64.3	19.36%	38.73%	58.09%	38.6	42.7
P, wt.%	0.061	0.005	0.051	0.072	0.045	0.077	8.59%	17.18%	25.77%	0.058	0.064
Pb, ppm	86	9	69	104	60	112	10.00%	20.01%	30.01%	82	91
Pr, ppm	10.1	0.45	9.2	11.0	8.8	11.5	4.41%	8.81%	13.22%	9.6	10.6

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion ICP continued											
Rb, ppm	169	6	156	182	150	188	3.79%	7.58%	11.38%	161	178
S, wt.%	0.716	0.049	0.618	0.813	0.569	0.862	6.83%	13.65%	20.48%	0.680	0.752
Sb, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Si, wt.%	29.67	0.551	28.56	30.77	28.01	31.32	1.86%	3.72%	5.57%	28.18	31.15
Sm, ppm	7.01	0.250	6.51	7.51	6.26	7.76	3.56%	7.12%	10.69%	6.66	7.36
Sn, ppm	16.1	2.7	10.8	21.4	8.1	24.1	16.58%	33.17%	49.75%	15.3	16.9
Sr, ppm	42.9	1.90	39.1	46.7	37.2	48.5	4.43%	8.86%	13.29%	40.7	45.0
Ta, ppm	1.21	0.21	0.78	1.64	0.57	1.86	17.72%	35.45%	53.17%	1.15	1.27
Tb, ppm	0.97	0.084	0.80	1.13	0.71	1.22	8.70%	17.40%	26.10%	0.92	1.01
Te, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	16.6	0.96	14.7	18.5	13.8	19.5	5.75%	11.50%	17.26%	15.8	17.4
Ti, wt.%	0.410	0.020	0.369	0.450	0.349	0.471	4.97%	9.93%	14.90%	0.389	0.430
Tl, ppm	0.89	0.028	0.84	0.95	0.81	0.98	3.10%	6.20%	9.30%	0.85	0.94
Tm, ppm	0.49	0.06	0.36	0.61	0.30	0.67	12.48%	24.96%	37.44%	0.46	0.51
U, ppm	3.32	0.158	3.01	3.64	2.85	3.79	4.75%	9.51%	14.26%	3.15	3.49
V, ppm	93	5.2	82	103	77	109	5.62%	11.23%	16.85%	88	98
W, ppm	< 7	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Y, ppm	28.6	0.99	26.6	30.6	25.7	31.6	3.47%	6.93%	10.40%	27.2	30.1
Yb, ppm	2.88	0.172	2.54	3.22	2.36	3.40	5.98%	11.95%	17.93%	2.74	3.02
Zn, ppm	358	23	312	404	289	427	6.43%	12.87%	19.30%	340	376

Note: intervals may appear asymmetric due to rounding

PREPARER AND SUPPLIER OF THE REFERENCE MATERIAL

Reference material OREAS 923 has been prepared and certified by:

ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.ore.com.au
Email: info@ore.com.au

It has been packaged in 10g units in laminated foil pouches.

INTENDED USE

OREAS 923 is intended for the following uses:

- for the monitoring of laboratory performance in the analysis of geological samples for the analytes reported in Table 1;
- for the verification of analytical methods for analytes reported in Table 1;
- for the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 923 has been prepared from mineralised and altered carbonaceous siltstones and mudstones from the CSA mine located near the town of Cobar in central western New South Wales, Australia. It has been packaged in robust foil laminate pouches and under normal storage conditions has long-term stability beyond 10 years.

INSTRUCTIONS FOR THE CORRECT USE OF THE REFERENCE MATERIAL

The certified values for OREAS 923 refer to the concentration level in its packaged state. It should not be dried prior to weighing and analysis.

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions such as the use of safety glasses and dust masks are advised.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

CERTIFYING OFFICER

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager – (ORE P/L)

REFERENCES

ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.

ISO Guide 35 (2006), Certification of reference materials - General and statistical principals.